

* NOTICES *

JPO and INPIT are not responsible for any
damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1](A) Denaturation polyvinyl alcohol whose denaturation rate by an anionic group is 2.0-40.0-mol %, and a water soluble film in which (B) mean particle diameter contains insoluble in water or poorly soluble impalpable powder of 150 micrometers or less.

[Claim 2]The water soluble film according to claim 1 being denaturation polyvinyl alcohol produced by said denaturation polyvinyl alcohol hydrolyzing into polyvinyl alcohol selectively or thoroughly after carrying out Michael addition of the vinyl compound.

[Claim 3]The water soluble film according to claim 1 being denaturation polyvinyl alcohol produced by said denaturation polyvinyl alcohol hydrolyzing into polyvinyl alcohol selectively or thoroughly after carrying out Michael addition of acrylonitrile or the acrylamide.

[Claim 4]Water-soluble wrapping which becomes any 1 paragraph of claims 1-3 from a water soluble film of a statement.

[Translation done.]